



GOLDEN EPOCH LTD
金國香港有限公司

GOLDEN EPOCH LIMITED

SPEC. COMPARISON
“PREMIUM COCOSHELL CHARCOAL”

Parameters	Unit	As Received	Dry Basis	Test Method	Target	Comparison
• Total Moisture	% wt	4.6	---	ASTM D 2961	10% (maximum)	(+) -10%
• Ash Content	% wt	1.5	1.6	ASTM D 3174-04	2% (maximum)	(+) -0,4%
• Volatile Matter	% wt	20.2	21.2	ASTM D 3175-02	15% (maximum)	(-) +6,2%
• Fixed Carbon	% wt	73.7	77.2	By different	72% (minimum)	(+) +5,2%
• Gross Calorific Value	Kcal/Kg	7110	7453	ASTM D 5865-04	5000 (minimum)	(+) +2.453

Comparative Values

Issued by : **PT. SUCOFINDO**
Reff # : **212/35/002161/07/2007**